Application Instructions

		TIME	TEMPERATURE (°C)	PRESSURE	PEEL
CAD-CUT® Heat Transfer Vinyl	FlexCut X Stretch	10 seconds/ 5 seconds	130°/ 150°	Medium	Hot
	FlexCut X	10 seconds/ 5 seconds	130°/ 150°	Medium	Hot
	FLEX CUT SBB MAXIMA	10 seconds	130°	Medium	Hot
	BlazeCut	10 seconds	150°	Medium	Cool
	Reflexcut HT	10 seconds	150°	Medium	Hot
	SiFlex	10 seconds	150°	Medium	Cool
	Metalflex	10 seconds	150°	Medium	Cool
	Royal pu	15 seconds	150°	Medium	Hot
	Ultra pu	10 sec for 1st press, peel COOL, 20 sec for 2nd press	150°	Medium	Cool
	GLITTER	10 seconds	150°	Medium	Hot
	Metalflex shine	10 seconds	150°	Medium	Cool
	Holographique	10 seconds	150°	Medium	Warm
	Crazyflex	12 seconds	160°	Medium	Cool
CAD-COLOR® Printable HTV	GRAFFITI Custom	10 seconds/ 5 seconds	130°/ 150°	Medium	Hot
	Tatoo SBB MAXIMA	10 seconds	140°	Medium	Hot
	Shimmerflex	12 seconds	160°	Medium	Cool
	Glowflex	12 seconds	150°	Medium	Hot
	Flex tape				
	Flock tape				

CUTTING NOTES
Always test cut prior to any production run. For optimal cutting and weeding, maintain a line thickness of at least 1/16” for lettering & logos.

CARE INSTRUCTIONS
Machine wash inside out using mild detergent. Do not use bleach. Dry at a normal dryer setting on household machines. Do not dry clean.

STORAGE
Store in a cool and dry area around 65 to 70 degrees Fahrenheit with 50% relative humidity. Keep away from direct heat, sunlight and humidity. Recommended shelf life is one year.